

ISO 12944-5 - Antiox - MonoGuard



Vejledende forbrugsguide til Antiox og MonoGuard specificeret i gr/m² og l/m²,
i henhold til ISO 12944-5

Husk altid at kontakte teknisk afdeling for vejledning
eller behandlingsforslag.


Produktinformation får du på www.acrymatic.dk

Consumption guide for Antiox og MonoGuard specified in gr/m² og l/m²,
according to ISO 12944-5

Always remember to contact the technical department for guidance
or treatment suggestions.

Product information is available at www.acrymatic.dk

– dokumentation får du på www.acrymatic.dk

System: Antiox - MonoGuard										ISO 12944-5						
	Paint System			Priming and Subsequent Coat(s)				TopCoat(s)				Durability				
	NDFT	MNOC		Product	Binder type	MNOC	NDFT	Product	Binder type	MNOC	NDFT	Low	Medium	High	Very high	
C2 - Low	80	2		Antiox	AY	1	40 µm / 87 gr	MonoGuard	AY	1	40 µm / 0,093 ltr					
Medium	130	2		Antiox	AY	1	80 µm / 174 gr	MonoGuard	AY	1	50 µm / 0,116 ltr					
High	175	2		Antiox	AY	1	100 µm / 217 gr	MonoGuard	AY	1	75 µm / 0,174 ltr					
Very High	200	2		Antiox	AY	1	120 µm / 261 gr	MonoGuard	AY	1	80 µm / 0,186 ltr					
C3 - Low	130	2		Antiox	AY	1	80 µm / 174 gr	MonoGuard	AY	1	50 µm / 0,116 ltr					
Medium	175	2		Antiox	AY	1	100 µm / 217 gr	MonoGuard	AY	1	75 µm / 0,174 ltr					
High	200	2		Antiox	AY	1	120 µm / 261 gr	MonoGuard	AY	1	80 µm / 0,186 ltr					
Very High	250	2		Antiox	AY	1	175 µm / 380 gr	MonoGuard	AY	1	80 µm / 0,186 ltr					
C4 - Low	175	2		Antiox	AY	1	100 µm / 217 gr	MonoGuard	AY	1	75 µm / 0,174 ltr					
Medium	200	2		Antiox	AY	1	120 µm / 261 gr	MonoGuard	AY	1	80 µm / 0,186 ltr					
High	250	2		Antiox	AY	1	175 µm / 380 gr	MonoGuard	AY	1	80 µm / 0,186 ltr					
Very High	300	2		Antiox	AY	1	220 µm / 478 gr	MonoGuard	AY	1	80 µm / 0,186 ltr					
C5 - Low	200	2		Antiox	AY	1	120 µm / 261 gr	MonoGuard	AY	1	80 µm / 0,186 ltr					
Medium	255	2		Antiox	AY	1	175 µm / 380 gr	MonoGuard	AY	1	80 µm / 0,186 ltr					
High	250	3		Antiox	AY	1	100 µm / 217 gr	MonoGuard	AY	2	150 µm / 0,349 ltr					
High	300	2		Antiox	AY	1	220 µm / 478 gr	MonoGuard	AY	1	80 µm / 0,186 ltr					
Very High																
Contact Acrymatic Coating for the right system in C5 - Very High																
AY: Acrylic paints.				MNOC: Minimum number of coats to get to NDFT.				gr: Gram.				ltr: Liter.				
NDFT: Nominal dry film thickness (Total amount of paint)													Stripe coat: Depends on the project.			
																
													Durability: Years to first major maintenance <7 years <15 years <25 years >25 years			

- Der tages forbehold for trykfejl / - Reservations are made for printing errors